

Technical Data Sheet

HA899J

Polypropylene, Homopolymer

Product Description

Viva Energy Polymers polypropylene grade HA899J is a high stiffness and high clarity homopolymer. Target applications for HA899J include extruded sheet and rigid packaging.

Status	Commercial: Active
Availability	Asia-Pacific; Australia and New Zealand
Application	Thermoformed Food Containers
Market	Rigid Packaging
Processing Method	Sheet; Thermoforming
Attribute	High Clarity; High Rigidity; Low Flow

Typical Properties	Nominal value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	2.5	g/10 min	ISO 1133-1
Density, (23°C, Method D)	0.90	g/cm ³	ISO 1183-1
Mechanical			
Flexural Modulus	2200	MPa	ISO 178
Tensile Stress at Yield	40	MPa	ISO 527-1, -2
Impact			
Notched Izod Impact Strength, (23 °C)	4.0	kJ/m ²	ISO 180/1A
Hardness			
Shore Hardness, (Shore D)	77		ISO 868
Thermal			
Vicat Softening Temperature	157	°C	ISO 306
Heat Deflection Temperature B, (0.45 MPa, Unannealed)	115	°C	ISO 75B-1, -2

Notes

These are typical property values not to be construed as specification limits.

Regulatory Status

For regulatory compliance information, see Product Stewardship Bulletin and Safety Data Sheet.

Company Information

For further information regarding Viva Energy please visit www.vivaenergy.com.au.

© VIVA ENERGY GROUP

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, Viva Energy may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a Viva Energy representative.