

Technical Data Sheet

HP422M

Polypropylene, Homopolymer

Product Description

Viva Energy Polymers polypropylene grade HP422M is a moderate flow polypropylene formulated with a general purpose additive package. HP422M is designed for the production of biaxially orientated polypropylene film on tubular double bubble lines and for cast film applications. HP422M is also suitable for injection moulding applications.

Status	Commercial: Active
Availability	Asia-Pacific; Australia and New Zealand
Application	Food Packaging Film; Lamination Film
Market	Consumer Products; Flexible Packaging
Processing Method	BOPP; Cast Film; Injection Moulding
Attribute	Homopolymer; Medium Flow

Typical Properties	Nominal value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	7	g/10 min	ISO 1133-1
Density, (23°C, Method D)	0.90	g/cm ³	ISO 1183-1
Mechanical			
Flexural Modulus	1400	MPa	ISO 178
Tensile Stress at Yield	31	MPa	ISO 527-1, -2
Impact			
Notched Izod Impact Strength, (23 °C)	3.5	kJ/m ²	ISO 180/1A
Hardness			
Shore Hardness, (Shore D)	75		ISO 868
Thermal			
Vicat Softening Temperature	154	°C	ISO 306
Heat Deflection Temperature B, (0.45 MPa, Unannealed)	82	°C	ISO 75B-1, -2

Notes

These are typical property values not to be construed as specification limits.

Regulatory Status

For regulatory compliance information, see Product Stewardship Bulletin and Safety Data Sheet.

Company Information

For further information regarding Viva Energy please visit www.vivaenergy.com.au.

© VIVA ENERGY GROUP

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, Viva Energy may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a Viva Energy representative.