

Technical Data Sheet

HP555G

Polypropylene, Homopolymer

Product Description

Viva Energy polypropylene grade HP555G is a low flow homopolymer with a conventional molecular weight distribution and is formulated with an enhanced process stability additive package. HP555G is designed for extrusion processes that demand high melt strength and melt stability characteristics. End use products typically made from HP555G include strapping, mechanically fibrillated yarns and profiles.

Status	Commercial: Active
Availability	Asia-Pacific; Australia and New Zealand
Application	Panels & Profiles; Strapping
Market	Industrial; Building & Construction; Rigid Packaging; Textile
Processing Method	Extrusion Blow Moulding; Sheet
Attribute	Good Melt Strength; High Melt Stability; Low Flow

Typical Properties	Nominal value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	1.3	g/10 min	ISO 1133-1
Density, (23°C, Method D)	0.90	g/cm ³	ISO 1183-1
Mechanical			
Flexural Modulus	1450	MPa	ISO 178
Tensile Stress at Yield	33	MPa	ISO 527-1, -2
Impact			
Notched Izod Impact Strength, (23 °C)	7.5	kJ/m ²	ISO 180/1A
Hardness			
Shore Hardness, (Shore D)	75		ISO 868
Thermal			
Vicat Softening Temperature	155	°C	ISO 306
Heat Deflection Temperature B, (0.45 MPa, Unannealed)	92	°C	ISO 75B-1, -2

Notes

These are typical property values not to be construed as specification limits.

Regulatory Status

For regulatory compliance information, see Product Stewardship Bulletin and Safety Data Sheet.

Company Information

For further information regarding Viva Energy please visit www.vivaenergy.com.au.

© VIVA ENERGY GROUP

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, Viva Energy may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a Viva Energy representative.