

# Technical Data Sheet

## HP744T

### Polypropylene, Homopolymer

#### Product Description

Viva Energy Polymers polypropylene grade HP744T is a high melt flow, ex-reactor nucleated homopolymer. HP744T has high stiffness, very low organoleptic properties and improved anti-tiger stripe performance. HP744T has been formulated for use in automotive, compounding and thin wall injection moulding applications, where rapid cycle times are required together with consistent performance and a balanced level of mechanical properties.

<b>Status</b>	Commercial: Active
<b>Availability</b>	Asia-Pacific; Australia and New Zealand
<b>Application</b>	Containers; TWIM Food Containers
<b>Market</b>	Rigid Packaging
<b>Processing Method</b>	Injection Moulding
<b>Attribute</b>	Fast Cycle (Production); Good Mouldability; High Flow; Homopolymer; Nucleated

Typical Properties	Nominal value	Units	Test Method
<b>Physical</b>			
Melt Flow Rate, (230 °C/2.16 kg)	70	g/10 min	ISO 1133-1
Density, (23°C, Method D)	0.90	g/cm <sup>3</sup>	ISO 1183-1
<b>Mechanical</b>			
Flexural Modulus	1950	MPa	ISO 178
Tensile Stress at Yield	38	MPa	ISO 527-1, -2
<b>Impact</b>			
Notched Izod Impact Strength, (23 °C)	2	kJ/m <sup>2</sup>	ISO 180/1A
<b>Hardness</b>			
Shore Hardness, (Shore D)	72		ISO 868
<b>Thermal</b>			
Vicat Softening Temperature	151	°C	ISO 306
Heat Deflection Temperature B, (0.45 MPa, Unannealed)	105	°C	ISO 75B-1, -2

## Notes

These are typical property values not to be construed as specification limits.

## Regulatory Status

For regulatory compliance information, see Product Stewardship Bulletin and Safety Data Sheet.

## Company Information

For further information regarding Viva Energy please visit [www.vivaenergy.com.au](http://www.vivaenergy.com.au).

© VIVA ENERGY GROUP

## Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, Viva Energy may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a Viva Energy representative.