

Technical Data Sheet

AMC7H

Cutback Bitumen Seal



Description

AMC7H is a specially formulated cutback bitumen seal designed for efficient spraying and good adhesion to prepared bases and stone. AMC7H is formulated, utilising Viva Bitumen high flash cutter and is not classified as dangerous good.

Applications

AMC7H is designed as a cutback bitumen to be used as a seal to waterproof and hold cover aggregate on prepared bases and existing roads. Application rates depend upon the class of road and the anticipated daily traffic, but will typically vary between 1.1 and 1.7 L/m².

Application Temperature	150 to 185 degrees C
Short Term Maximum Temperature	180 °C
Long Term Storage Temperature	140 °C
Maximum Safe Temperature	190 °C

Health & Safety

AMC7H is unlikely to present any significant health or safety hazard when properly used in the recommended application where good standards of industrial practice are maintained.

Further guidance on Product Health and Safety is available on the relevant Material Safety Data Sheet

Specifications/approvals

AS 2157	Sealing Class AMC7
---------	--------------------

Typical characteristics

Description	Units	Methods	Typical
Viscosity at 60° C	Pa.s	AS 2341.2	43.0 to 86.0
Flashpoint	degrees C	AS 2341.16	> 61.5
Residue from distillation to 360° C, volume by difference	%	AS 2341.15	96