

# Technical Data Sheet

## Viva Bitumen Primer 1500H

### Special cutback primer binder



#### Description

Viva bitumen Primer 1500H is a special cutback bitumen primer seal containing additives to improve the adhesion of the bitumen to a prepared base. Primer 1500H is designed for to seal a pavement immediately after construction and preparation and hold the pavement in good condition until the final bituminous surface is applied. Primer 1500H utilises Viva Bitumen high flash cutter and is **not** classified as a dangerous good.

#### Applications

Viva bitumen Primer 1500H is designed as a primer binder for application on newly prepared surfaces. Suitable application rates range from 1.0 to 1.7 L/m<sup>2</sup>.

Application Temperature	110 to 135 degrees C
Short Term Maximum Temperature	140 °C
Long Term Storage Temperature	90 °C
Maximum Safe Temperature	140 °C

#### Health & Safety

Viva bitumen Primer 1500H is unlikely to present any significant health or safety hazard when properly used in the recommended application where good standards of industrial practice are maintained.

Further guidance on Product Health and Safety is available on the relevant Material Safety Data Sheet

#### Specifications/approvals

Viva bitumen Primer 1500H is a proprietary product

#### Typical characteristics

Description	Units	Methods	Typical
Viscosity at 60° C	Pa.s	AS 2341.2	1.5 to 3.0
Flashpoint	degrees C	AS 2341.16	> 61.5
Residue from distillation to 360° C, volume by difference	%	AS 2341.15	84